

MAXMET 100 EPOXY METAL REPAIR & REBUILDING COMPOUND

Description	MAXMET 100 EPOXY METAL REPAIR COMPOUND Is a multi-purpose, solvent free, epoxy metal repair and rebuilding compound. The product is suitable for repairing, metal components suffering material loss due to mechanical damage, erosion, corrosion and wear.
--------------------	--

Applications	<ul style="list-style-type: none"> • Worn or damaged pump shafts • Filling pitting corrosion • Resurfacing pump housings • Cracked pump or valve casings • Scored hydraulic rams • Worn bearing housings • Damaged flanges • Leaking tank seams • Worn keyways • Cracked engine blocks • Structural adhesive
---------------------	---

Surface Preparation Steel	<p>All oil and grease must be removed from the surface of the repair using an appropriate cleaner such as MEK or similar solvent. For optimum performance, the surface should be grit-blasted to ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2) and a minimum blast profile of 75 microns using an angular abrasive.</p> <p>Once blast cleaned, the surface must be degreased and cleaned using MEK or similar solvent. All surfaces must be repaired before gingering or oxidation occurs</p>
----------------------------------	--

Surface Preparation Salts	<p>For salt contaminated surfaces the area must be grit-blast cleaned as mentioned above and left for 24 hours to allow any ingrained salts to come to the surface.</p> <p>After this 24-hour period the surface must be washed with MEK prior to brush blasting to remove the surface salts. This process must be repeated until all ingrained contaminants have been sweated out of the surface.</p>
----------------------------------	--

MAXMET 100 EPOXY METAL REPAIR & REBUILDING COMPOUND

Cracks

In the case of cracked surfaces, the cracks should be stabilised by drilling the termination points and the cracks ve-ed out and drilled, tapped and bolted every 75 -100 mm.

Mixing

Warm the Base component to 15-25°C before mixing and do not apply when the ambient or substrate temperature is below 5°C or less than 3°C above dew point. Mix both Part-A and part-B together in full units as supplied.

For small quantities us a mixing ratio of:

3:1 by volume or **5:1** by weight

When mixing both materials, it is very important to have a uniform grey paste that is streak free. Once mixing is complete, use the mixed paste as soon possible after mixing.

Application

Apply the mixed material directly to base coat as soon as possible after the application but not exceeding 6 hours, using a short-bristled brush, spatula, squeegee or plastic applicator.

Single coat application thickness 0-20mm

Coverage

1kg unit of mixed product will cover 0.406 sq metres at a nominal thickness of 1.0mm

Over-Coat Times

Minimum – the applied material can be over-coated as soon as it is touch dry.

Maximum – over-coating time **6 hours**.

Where the maximum over-coating time is exceeded, the material should be allowed to harden before being abraded, or flash-blasted and solvent washed to remove any surface contamination

MAXMET 100 EPOXY METAL REPAIR & REBUILDING COMPOUND

**Pot Life @
20°C**

20 - 25 minutes

**Health and
Safety**

Please ensure good practice is always observed during the mixing and application of this product.

Protective gloves must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read the fully detailed Material Safety Data Sheet.

**Legal
Notice**

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control.

It is the responsibility of the customer to determine the products suitability for use.

Maxkote accepts no liability arising out of the use of this information or the product described herein.